TECHNICAL DATASHEET

YELLOW 967

CHEMICAL CHARACTERISTICS

	στανισά
Form	powder
Specific gravity (g/cm ³)	5,6
Lead Chromate	

Dibutyl phthalate 5

	•	
SPECIFIC DATA Oil absorption Temperature resistance	STANDARD 14 200°C	TEST METHOD DIN 53199 DIN 53775
Lightfastness masstone tint	7 7-8	DIN 54003
Weatherfastness	4	DIN 54001
Resistance to acids	4	DIN 54001
Resistance to alkalis	4	DIN 54001
Fastness to re-coating (bleeding)	5	DIN 54002
Fastness to solvents		
water	5	
Butanol	5	
Ethyl glycol	5	
Butyl acetate	5	
Methyl ethyl	5	
ketone	-	
White spirit	5 5	
Xylene	5	

The information given is based on our actual knowledge of the product, it is not a guarantee. The client should test the product, several elements might affect the use and the applications. Existing laws and directives have to be respected by the client under his own responsibility.

(DIN 53193) at

20°C