## **TECHNICAL DATASHEET**

## **ORANGE 971**

## **DESCRIPTION**

**MOLYBDATE ORANGE 971** 

## **CHEMICAL CHARACTERISTICS**

LEAD CH	ΙK	Οľ	VIF	٩I	E
---------	----	----	-----	----	---

Fastness to solvents

water

Specific gravity (g/cm³) 5.6 (DIN 53193) at 20°C

Form powder

SPECIFIC DATA Oil absorption Temperature resistance	STANDARD 15 240°C	<b>TEST METHOD</b> DIN 53199 DIN 53775
Lightfastness masstone tint	6-7 7	DIN 54003
Weatherfastness	4	DIN 54001
Resistance to acids	3	DIN 54001
Resistance to alkalis	3	DIN 54001
Fastness to re-coating (bleeding)	5	DIN 54002

5

The information given is based on our actual knowledge of the product, it is not a guarantee. The client should test the product, several elements might affect the use and the applications. Existing laws and directives have to be respected by the client under his own responsibility.